

## Montage-Brandschutzschaum

### Product Description

Moisture-reactive one-component polyurethane foam system from the aerosol can. For processing with enclosed adapter tube. Full yield and optimal foam structure is achieved only by sufficient shaking and moistening. Free from CFC, HCFC and HFC.

### Product Properties

- B1 "hardly inflammable" according to DIN 4102-1
- "no burning particles/drops dripping off" according to DIN 4102-16
- hardly inflammable straw foam
- easy and fast processing
- dimensionally stable
- no dwell pressure after curing
- heat insulating
- safe in the cured condition
- resistant to aging - but not to UV radiation
- frost resistant
- high bonding strength on most building substrates such as masonry, concrete and wood, on insulating materials, metals and many plastics
- excellent adhesion to wood, fiber cement, aerated concrete, concrete, masonry, plaster, XPS and rigid PVC
- easy to rework e.g. cutting, sawing, as well as plastering, painting and papering on top



### Areas of Application

windows, roof windows, attic conversion, doors, partition walls, precast walls, roller shutter boxes, air conditioning and ventilation systems, joints in thermal insulation systems, pipelines, metal structures, wooden structures

### Form of Delivery

Foam color: yellowish  
Packing unit: 6 cans per box  
Can: 750 ml

## Substrates

---

### Suitable substrates:

masonry, plaster, wood, concrete, aerated concrete, bricks, clinker, plasterboards, fiberboards, various plastics, corrosion-protected metals, styrofoam, various other insulating materials, ceramics, tiles, stone

### Unsuitable substrates:

PE, PP, PTFE, oily/greasy surfaces, gypsum, tar, bitumen, silicone, corrosion-prone metals, some powder coatings, release agents

## Instructions for Use

---

The adhesive surfaces must be clean, free from release agents and stable. Dust, grease, oil and loose parts must be removed before processing. For gypsum-based substrates, a suitable gypsum primer is recommended. Moisten dry surfaces before foaming. Metals must be provided with a protective coating to prevent corrosion damage due to moistening prior and after application. Cover adjacent areas sufficiently and put on personal protective clothing. Shake the can well at least 20 times before use. Remove cover/safety cap. Screw the enclosed adapter tube onto the can and foam sparingly/dosed.

After foaming the foam should be sprayed again with water. This accelerates the reaction and ensures optimal curing. The optimum can temperature is 20 °C. Deformation-sensitive components must be adequately supported until complete curing of the foam. Low temperatures slow curing significantly. Substrates must have temperatures of over 0 °C during the entire curing time. The gap widths should not be less than 5 mm and not more than 30 mm. For joints over 30 mm, possibly foam in several layers.

For relevant fire protection applications, the specifications of the manufacturers and the applicable standards have to be observed. In case of doubt, please contact our sales staff before application.

## Technical Data

Characteristics	Standard	Value
Fire behavior	DIN 4102-1	class B1
Dripping behavior	DIN 4102-16	no burning particles/drops dripping off
Processing temperature can min./max.		+5 to +30 °C
Processing temperature can optimal		+15 to +25 °C
Processing temperature environment min./max.		+5 to +35 °C
Processing temperature environment optimal		+15 to +25 °C
Yield free-foamed (20 °C/65 % RLF)	FEICA EN 17333	approx. 32 liters / 750 ml can
Skin forming time (20 °C/65 % RLF)		approx. 8 - 10 minutes
Cutttable at string thickness 2 cm (20 °C/65 % RLF)		approx. 35 minutes
Resilient after (20 °C/65 % RLF, moistened)		approx. 5 hours
Form stability (20 °C/65 % RLF)	FEICA EN 17333	± 5 %
Temperature resistance		-40 to +80 °C short term +120 °C
Bulk density SKZ method		approx. 28 kg/m <sup>3</sup>
Compressive strength at 10 % compression	DIN 53421	7 - 9 N/cm <sup>2</sup>
Thermal conductivity	EN 12667	approx. 0,035 W/mK
Shelf life (dry, at 20 °C); higher temperatures shorten the storage time		12 months

## Safety Instructions

Wear gloves during processing as the fresh foam sticks strongly and can only be removed mechanically after hardening. Wear safety glasses. Remove fresh foam splashes with INSEBO PU-Universal-Reiniger. Hardened PU foam can only be removed mechanically.

Store upright and cool otherwise the valve may stick. Higher temperatures shorten the storage time.

Please refer to our safety data sheet and the product label for further information on product safety and handling.

Current safety data sheets and further information on our products can be found at [www.insebo.com](http://www.insebo.com).

## Service

---

Upon request, our trained sales representatives are always at your disposal.

## Disposal

---

For disposal instructions please refer to our safety data sheet and product label.

## Additional Information

---

This technical data sheet advises without obligation and guarantee. The mentioned processing instructions have to be adapted to the prevailing conditions. The user is obliged to check the suitability and application by own experiments in order to avoid failures.

All given descriptions, data, ratios, weights, etc. can change without notice and do not represent contractually agreed properties of the product. Existing laws, standards and regulations are to be observed by the recipient of our products in their own responsibility.

Due to the large number of possible influences during processing and application, a guarantee of certain properties or suitability for a specific application can not be made, own tests are necessary.

The right to make technical changes is reserved.

## Test Certificates

---

<b>DIN 4102-1</b>	<b>Class B1 (hardly inflammable)</b>
<b>DIN 4102-16</b>	<b>„no burning particles/drops dripping off“</b>
Testing institute:	CSI Prag
Test report:	16/397/P147-1
Int. PZ-No.:	PU 173